

## Quik Cure

### Acrylic Based Curing Membrane



#### DESCRIPTION:

- 100% Non tintable acrylic-based curing membrane over cementitious surfaces.
- Provides a sound, sealed substrate for a uniform finish over either stucco or concrete.
- Improves coverage of the finish.
- Increased adhesion. Improves the mechanical bond of the finish.
- Superior resistance to mold, mildew and efflorescence.

#### USES:

- Recommended as a surface preparation for stucco, masonry, drywall, plaster, concrete tilt wall and concrete poured in place.
- Allows acrylic finishes to be applied quickly: as early as 2 hours after application of Parex USA Quik Cure.
  - Enhances the appearance and uniformity of the finish.

#### COMPOSITION:

- Single component liquid
- Color: dries clear
- Water-based: VOC compliant

#### COVERAGE:

900-1,200 sq. ft. (84-111 sq. m)/5 gallon pail depending on the porosity of the stucco base.

#### CONTAINER:

In 5 gallon pails.

- Storage: Protect from sun and freezing at all times
- Do not stack more than 3 pails high
- Shelf Life: Reference Parex USA Expiration Date of Products Technical Bulletin.

#### DRYING TIME:

Approximately 1/2 hour to 2 hours depending on temperature, humidity, and substrate.

#### CLEAN-UP:

Water soluble prior to drying. Clean tools and containers with water prior to drying.

#### SURFACE PREPARATION:

- Remove surface contaminants such as dust or dirt without damaging the substrate.
- For previously painted surfaces, all loose and chalking paint must be removed, and glossy surfaces dulled.
- New concrete and masonry must be clean and cured a minimum of 28 days.
- Parex USA Portland Cement Plaster must be clean and moist cured for 48 hours and allowed to dry an additional 48 hours before application of Parex USA Quik Cure.
- Other Portland Cement Plasters must be clean and cured a minimum of 7 days.
- Check concrete surfaces for alkalinity and treat. Any form-release agents or bond breakers must be removed.
- Uneven concrete or masonry can be leveled with either Parex USA Base Coat or Adhesive and Base Coat or other suitable, compatible product.
- For additional options, contact Parex USA Technical Services Department.

#### MIXING:

- Use clean equipment for mixing and preparation.

- Mix thoroughly. Only a small amount of clean potable water can be added.

#### APPLICATION:

- Read the entire label before using this product.
- Apply with a roller, brush or suitable spray equipment in a continuous coat.
- Parex USA Quik Cure must be completely dry before any Parex USA finish is applied.
- Keep container closed when not in use.

#### LIMITATIONS:

- Ambient and surface temperature must be 40°F (4°C) or higher during application and drying time. Provide supplemental heat and protection from precipitation as needed.
- Use only on surfaces that are sound, clean, dry, unpainted and free from any residue which may affect the ability of the Parex USA Quik Cure to bond to the surface.
- Avoid application in direct sunlight in hot weather.
- Quik Cure is not to be used as an admixture.

#### WARNING

- Read complete Warning information printed on product container prior to use. For medical emergency information, call 1-800-424-9300.
- For more information on handling this product refer to its Material Safety Data Sheet (MSDS). The most current MSDS and Product Data Sheet (PDS) can be found on our website.
- This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about the guidelines for the proper use and application of the covered product(s) under normal environmental and working conditions. Because each project is different, Parex USA, Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

Parex USA, Inc.  
4125 E. La Palma Ave., Suite 250  
Anaheim, CA 92807  
(866) 516-0061 Tech Support: (800) 226-2424

**Facilities**  
French Camp, CA  
North Hollywood, CA  
Riverside, CA  
San Diego, CA

Colorado Springs, CO  
Haines City, FL  
Duluth, GA  
Redan, GA

Albuquerque, NM  
Allentown, PA  
San Antonio, TX

