

Fastwall Sanded

DESCRIPTION

- A fiber reinforced stucco base
- Factory prepared mixture of Portland cement, fibers, sand and proprietary ingredients
- Can be installed 3/8-1/2 in. (9.5-12.7mm) thick in one application
- Color: Gray

USES

Stucco Base over:

- Concrete
- Masonry
- Metal lath

Lath is applied over:

- Appropriate water resistive barrier over continuous sheathing
- Expanded polystyrene (EPS)

COMPOSITION

- Binder: Portland cement
- Synthetic fibers
- Mineral and organic additives

MATERIAL STANDARDS

Cement: ASTM C150

Lime: ASTM C206

Fibers: ASTM C1116

PROPERTIES

Meets code criteria for exterior cementitious coating.

ICC-ES Report ESR-2564 includes 1 hour fire-resistive assemblies.

COVERAGE

Depending on the condition of the substrate and thickness of application approximate coverages per bag are:

- at 3/8 in. (9.5mm): 20-25 ft² (1.9-2.3 m²)
- at 1/2 in. (12.7mm): 15-19 ft² (1.4-1.8 m²)
- Coverage may vary due to ambient temperature, surface temperature, surface porosity, mixing methods, application methods, amount of water, wall type and metal lath type. Coverage must be verified in the field using the same procedures and conditions that will be present at the project.

CONTAINER

80 lb (36 kg) net weight in a moisture resistant bag.

- Storage: Store off ground and protect from rain and moisture
- Shelf Life: Reference ParexUSA Expiration Date of Products Technical Bulletin.

WORKING TIME

Sets in 30-45 minutes after mixing, depending on conditions.

SURFACE PREPARATION

- On masonry and concrete, apply only to surfaces that are sound, clean, dry, unpainted, and free of any residue

which may affect the ability of El Rey Fastwall to bond to the surface.

- Substrate shall have sufficient suction (ability to absorb water) or surface roughness or both to ensure an adequate bond for El Rey Fastwall Sanded.
- On lathed construction, apply to lathing installed in accordance with ASTM C1063.
- El Rey Fastwall requires water-resistive barrier installed and flashed in accordance with building code and to form a water-shedding surface. Stucco is not a water-resistive barrier.
- Install water-resistive barrier (type and method of application) per Specifications or ParexUSA Stucco Application Guide.
- Do not apply to substrates which are frozen or contain frost or ice.
- Apply to surface prepared as for Portland cement plaster.
- For additional surface preparation options, contact ParexUSA Technical Support.

MIXING

- Use clean equipment for mixing and preparation.
- Mixing ratio: approximately 1.5 gal (5.6L) water per 80 lb (36 kg) bag. First add approximately 90% of needed water in the mixer, then add the El Rey Fastwall Sanded. When mixture becomes homogeneous, add remaining water.

Test	Method	ICC AC 11 Testing Criteria	Results
Accelerated Weathering	ASTM G153	2000 Hours	No cracking, checking, crazing, erosion, or chalking.
	ASTM G155	2000 Hours	No cracking, checking, crazing, erosion, or chalking.
Flexural Strength	ASTM C348	No AC 11 Requirement	623 psi
Freeze-Thaw	ICC AC 11	10 cycles	No cracking, checking or crazing
Transverse Loads	ICC AC 11	Allowable design loads	Refer to ESR 2564
Drainage	ICC AC 11	90% Efficiency required when EPS is used	Pass. Refer to ICC-ES ER-2564 for listed assemblies
Surface Burning Characteristics	ASTM E84	Flame spread <25, Smoke Developed <450	Flame Spread: 0 Smoke Developed: 0
Fire Resistance	ASTM E119	One hour fire resistive rating	Pass. Refer to ICC-ES ESR-2564 for listed assemblies
Combustibility	ASTM E136	Noncombustible Material	Pass
Multi-Story Fire Evaluation	UBC 17-6	Required for Non-combustible Construction	Pass. Refer to ICC-ES ESR 2564 for assembly
Radiant Heat Exposure	NFPA 268	Required for Non-combustible Construction	Pass. Refer to ICC-ES ESR 2564 for assembly

** These are typical laboratory test results but do not constitute a specification.

- Mix at low speed for a minimum of 3 minutes, until the mixture is smooth.
- Do not overmix; never mix more than five minutes. Mix each batch for the same amount of time. Mix batches of the same size, using the same amount of water, to ensure consistency.
- Use cool, potable water at a uniform temperature above 40°F (4°C). Let hose run to clear it of hot water.
- Use El Rey Fastwall Sanded immediately after mixing.
- Do not retemper El Rey Fastwall.
- For enhanced performance use ParexUSA Adacryl Acrylic Admix & Bonder: As an admix: Use up to 1 qt (1.0L) per bag of El Rey Fastwall. After the dry components and the majority of the water has been mixed, add the acrylic admix in place of 1 qt. (1.0L) of water. Mix no longer than required to provide a uniform mixture. DO NOT OVERMIX. Over-mixing entrains excessive amounts of air which weaken the material. Do not re-temper mixes over 20 minutes old.
- Only ParexUSA approved additives may be added to this product.

NOTE: If ParexUSA Adacryl is mixed into El Rey Fastwall Sanded and El Rey Premium Stucco Finish is used, then ParexUSA Adacryl must be used in the El Rey Premium Stucco Finish also. No unapproved additives are allowed.

APPLICATION

- Read the entire label before using this product. For complete application procedures refer to ICC-ESR 2564.
- Thoroughly dampen concrete and masonry substrate if necessary before applying El Rey Fastwall Sanded.
- Apply by hand trowel or plaster gun to a minimum 3/8 in. (9.5mm) thickness. The maximum thickness applied in one pass should be 1/2 in. (12.7mm).
- Level the surface directly after application or score the surface of the un-set plaster to provide a key for a subsequent coat. If applying El Rey

Fastwall at a thickness greater than 1/2" or for large ceiling areas apply a second coat after allowing the first coat to dry.

- If additional El Rey Fastwall is not applied the same day, moisten the dry El Rey Fastwall as necessary before applying second coat.
- Keep stucco basecoat moist by fogging walls with water for the first 24-48 hours after initial hardening. Moist curing must be increased in dry weather and may be reduced in damp weather. Moist curing replaces mix water lost to evaporation and absorption. It improves hydration for strength and reduces volume-loss stresses. Insufficient moist curing can be a cause of cracking. Beyond 24 hours, additional moist and dry curing may also be needed to provide sufficient strength to the basecoat to resist the pressure of finish coat application.
- After moist curing, allow the stucco basecoat to air dry.
- For Portland cement-based stucco finish, lightly moisten the surface of El Rey Fastwall before application.

LIMITATIONS

- Ambient and surface temperature must be 40°F (4°C) or higher during application and drying time. Protect from freezing for a period of not less than 24 hours after set has occurred. Provide supplemental heat and protection from precipitation as needed.

- Ambient and surface temperatures must not exceed 120°F (49°C) during application and 24 hours after application.
- Avoid application in direct sunlight in hot weather. See packaging for handling precautions.
- For application to very dense or smooth concrete, contact ParexUSA Technical Support for additional information.

WARNING

- Read complete Warning information printed on product container prior to use. For medical emergency information, call 1-800-424-9300.
- For more information on handling this product refer to its Safety Data Sheet (SDS). The most current SDS and Product Data Sheet (PDS) can be found on our website.
- This Product Data Sheet has been prepared in good faith on the basis of information available at the time of publication. It is intended to provide users with information about the guidelines for the proper use and application of the covered product(s) under normal environmental and working conditions. Because each project is different, ParexUSA, Inc. cannot be responsible for the consequences of variations in such conditions, or for unforeseen conditions.

Level, Primer or Finish Coat	Recommended Moist Cure (hours)	Min. Additional Air Dry after Moist Cure
ParexUSA Stucco Level Coat with or without Fiber-glass Reinforcing Mesh.	24	1 day
ParexUSA Portland Cement-Based Stucco Finish *Dampen surface immediately prior to Portland cement-based stucco finish application. Primer is never allowed behind Portland cement-based stucco finish.	24	1 day
ParexUSA Acrylic Finish with ParexUSA Primer *Finish may be applied as soon as primer is dry.	24	1 day
ParexUSA Acrylic Finish without primer.	48	1 day
ParexUSA Elastomeric Finish with ParexUSA Primer.	48	3 days
ParexUSA Elastomeric Finish without primer.	48	5 days

*Longer moist cure and extended dry times may give better results.

PAREXUSA

Parex USA, Inc., a California Corporation
4125 E. La Palma Ave., Suite 250
Anaheim, CA 92807

www.parexusa.com
866-516-0061 Tech Support: 800-226-2424